

**A STUDY ON COMPRESSIVE STRENGTH OF MULTI BLEND CONCRETE
OF M20 GRADE**M PRAVEEN KUMAR¹, MALEPATI NAGARJUNA²¹ Assistant Professor, Dept. of Civil Engineering, Visvodaya Engineering college, Kavali, Nellore(District), Andhra Pradesh, INDIA.² Postgraduate student, Dept. of Civil Engineering, Visvodaya Engineering college, Kavali, Nellore(District), Andhra Pradesh, INDIA.

Abstract: The production of cement results in production of greenhouse gases in atmosphere, which will leads for global warning. Hence, the researchers are currently focusing on use of waste materials which are having cementing properties, which can be replaced in concrete as partially for cement, without comprising on its strength and durability, which will result in decrease of cement production thus reduction in emission of greenhouse gases, in addition to sustainable management of the waste. The properties of concrete mainly depend on the constituents used in concrete. The waste product like fly ash, Ground Granulated Blast Furnace slag (GGBS), silica fume, metakaolin etc. which has cementitious properties was used as partial replacement material for cement. This paper presents a study on mechanical properties of concrete made with multi component cement i.e., cement is blended with optimum.% of fly ash, Ground Granulated Blast Furnace slag (GGBS), silica fume & metakaolin. Study includes concepts of multi blended cement exploits the Compressive strength of multi blend concrete.

1. Introduction

Fly ash, Ground Granulated Blast furnace Slag, Silica fume, Metakaolin and many others, are some of pozzolanic substances which can be used as partially alternatives for cement in concrete. In present study i.e., Multi Blended Concrete is concrete in which binding multiple numbers of components. At gift look at, cement is blended with four components, namely Fly ash, GGBS, Silica Fume & Metakaolin. The fly ash, GGBS & silica fume materials are through products life, manufacture of metallic & silicon alloys respectively, whereas metakaolin is dehydroxylated form of clay mineral kaolinite. In present investigation studied about compressive strength of MULTI BLEND CONCRETE.

2. Materials and Their properties**2.1. Cement**

In the present investigation, commercially available 53 Grade ordinary Portland cement supplied by Zuari Cement, having Sp. Gravity 3.15, fineness modulus is 290 m²/kg, Normal consistency is 30%, initial setting time 45mins, final setting time is 6hr. 40min. and compressive strength of mortar is 54.2 MPa.

2.2. Fly ash

Fly ash conforming to the requirements of IS 3812 and IS 1727 (1967) and produced from RTPP muddanur (class F i.e., low calcium fly ash) with Specific gravity of 2.2 and specific surface area of fly ash 280 m²/ kg was used as supplementary cementitious material in concrete mixtures. 85% of particles are passed through 45µm sieve.

2.3. Ground Granulated Blast Furnace Slag (GGBS)

In this present investigation, commercially available GGBS particle size less than 20 micro meters was supplied by ASTRRA chemicals pvt. Limited, Chennai with specific gravity 2.85 was used for all concrete mixtures. Specific surface area of GGBS used in present investigation is 390 m²/ kg.

2.4. Silica fume

Silica fume used in present investigation is densified silica fume for good results. Silica fume is bought from AASTRRA Chemicals Pvt. Ltd. from Chennai. The specific gravity of used silica fume is 2.2. Specific surface of Silica fume 15,000 to 30,000 m²/ kg.

2.5. Metakaolin

Metakaolin is a dehydroxylated form of the clay mineral Kaolin or china clay. Stone which are rich in Kaolin are called China clay or Kaolin, traditionally used inside the manufacture of porcelain. The particle length of Metakaolin is smaller than cement debris, but not as first-rate as silica fume. Metakaolin used on this present experimental have a look at is acquired from ASTRRA chemical substances, Chennai. The specific gravity of Metakaolin is 2.2 with spherical shape of particles.

2.5. Aggregates

Aggregate properties greatly influence the behavior of concrete, since they occupy about 80% of the total volume of concrete. The aggregate are classified as

(I) Fine aggregate

(II) Coarse aggregate

Properties of sand are fine aggregates i.e., sand are specific gravity with 2.65, fineness modulus with 2.83(zone-II) and water absorption with 1%.

Properties of 20mm coarse aggregate are specific gravity with 2.76 and water absorption 0.5%

3. MIX DESIGN

For required, designed according to IS10262-2009. For a target mean strength of 26.6 N/mm^2 , the water/binder ratio with medium workability condition equal to 0.5 (for moderate exposure) was considered from IS 10262-2009. The mix proportion is as follows

Water : Cement : Fine aggregates : Coarse aggregate

176 : 352 : 717.69 : 1220.085

0.5 : 1 : 2.03 : 3.46

4. OBJECTIVES

- The main objective of the study is to use waste materials produced from industries and to reduce environmental pollution.
- To find the optimum content of the fly ash, GGBS, silica fume & metakaolin used in different proportions for increasing the compressive strength.

5. EXPERIMENTAL PROGRAM

The Concrete combos have been produced at a constant water/Cement ratio of 0.5 and one conventional concrete mix and 14 different combinations with exceptional percentages of fly ash, GGBS, silica fume and metakaolin are organized as mixture also. Initially for control mixture workability is found, then 3 cubes were casted, tested for 7 days, 14 days and 28 days. Same is done for other concrete mixtures in which cement is partially replaced with fly ash, GGBS, silica fume and metakaolin. Cement is partially replaced with materials for optimum dosages of fly ash, GGBS, silica fume and metakaolin

Initially cement is replaced with fly ash, and then to the optimum replacement of FA, GGBS will be added in varying proportions. To the optimum replacements of FA and GGBS, SF is added in varying proportions as partial replacement, and from this we will get optimum replacement of SF. Finally Metakaolin is replaced partially in cement along with optimum replacements of FA, GGBS, and SF. Summary of % of replaced binding material is given in table1

Table 1 Summary of % of replaced binding material

	Cement (%)	FA (%)	GGBS (%)	SF (%)	Metakaolin (%)
N	100				
NF1	90	10	0	0	0
NF2	80	20	0	0	0
NF3	70	30	0	0	0
NF4	60	40	0	0	0
NF2G1	75	20	5	0	0
NF2G2	70	20	10	0	0
NF2G3	65	20	15	0	0
NF2G4	60	20	20	0	0
NF2G2S1	67.5	20	10	2.5	0
NF2G2S2	65	20	10	5	0
NF2G2S3	62.5	20	10	7.5	0
NF2G2S1M1	65	20	10	2.5	2.5
NF2G2S1M2	62.5	20	10	2.5	5
NF2G2S1M3	60	20	10	2.5	7.5

FA	: Fly Ash
GGBS	: Ground Granulated Blast-furnace Slag
SF	: Silica Fume
N	: Normal concrete
NF1	: Normal concrete with 10% Fly ash
NF2	: Normal concrete with 20% Fly ash
NF3	: Normal concrete with 30% Fly ash
NF4	: Normal concrete with 40% Fly ash
NF2G1	: Normal concrete with 20% Fly ash and 5% GGBS
NF2G2	: Normal concrete with 20% Fly ash and 10% GGBS
NF2G3	: Normal concrete with 20% Fly ash and 15% GGBS
NF2G4	: Normal concrete with 20% Fly ash and 20% GGBS
NF2G2S1	: Normal concrete with 20% Fly ash, 10% GGBS and 2.5% silica fume.
NF2G2S2	: Normal concrete with 20% Fly ash, 10% GGBS and 5% Silica fume.
NF2G2S3	: Normal concrete with 20% Fly ash, 10% GGBS and 7.5% Silica fume.
NF2G2S1M1	: Normal concrete with 20% Fly ash, 10% GGBS, 2.5% Silica fume and 2.5% Metakaolin.
NF2G2S1M2	: Normal concrete with 20% Fly ash, 10% GGBS, 2.5% Silica fume and 5% Metakaolin.
NF2G2S1M3	: Normal concrete with 20% Fly ash, 10% GGBS, 2.5% Silica fume and 5% Metakaolin.

6. EXPERIMENTAL RESULTS

6.1. Non Destructive Testing method: Rebound Hammer Test

In present paper compared the results of compressive strength by using Rebound hammer test for MULTI BLEND CONCRETE with normal concrete at 28 days of curing. Results are tabulated in table 2.

Table 2 Compressive Strength values from Rebound Hammer Test

Type of concrete	Average compressive cube strength (MPa)
Normal concrete (N)	27.22
Multi blended concrete (NF2G2S1M1)	31.33

6.2. Compressive Strength

Compressive strength of concrete is found in laboratory by using compressive testing machine at age of 7days, 14days and 28days of curing. The results are tabulated in table 3. The results are shown for optimum replacement of blended materials. The remaining proportions of blended materials which are shown in table 1 are less in compressive strength when compared to the normal concrete. Variation of graph for optimum % replacement of blended materials is shown in Fig.1

Table 3 Compressive strength by using CTM

Mix proportion	7 Days (MPa)	14 Days (MPa)	28 Days (MPa)
N	17.2	21.50	25.80
NF2	16.9	20.90	27.80
NF2G2	17.4	21.85	28.00
NF2G2S1	18.2	23.70	28.30
NF2G2S1M1	18.2	23.70	28.30

CTM: Compressive Testing Machine




Fig. 2. Variation of compressive strength

7. DISCUSSIONS

7.1. Non-destructive testing method: Rebound hammer test

- The compressive strength of MULTI BLEND CONCRETE through the use of rebound hammer is improved by 15.09% when compared with the Normal concrete examined by using rebound hammer test on the age of 28days.
- The compressive strength of Normal concrete through the use of rebound hammer test is increased by means of 5.5% when as compared with the Normal concrete examined in compressive testing machine at the age of 28days.
- The compressive strength of MULTI BLENDED CONCRETE with the aid of the usage of rebound hammer is increased by 10.3% when compared with the MULTI BLEND CONCRETE tested in compressive testing machine at the age of 28days.

7.2. Compressive strength

- The compressive strength of concrete is increased upto a maximum of 7.75% at 20% replacement fly ash in cement content for 28 days of curing. By further addition of flyash, the compressive strength is reduced. The Compressive strength in early days has reduced when compared to normal concrete.
- The compressive strength of concrete is increased upto a maximum of 1.14 %, 1.62% and 8.52% at 20% replacement fly ash and 10% replacement of GGBS in cement content at 7 days, 14days and 28 days of curing respectively. By further addition of GGBS to the 20% fly ash replaced cement, the compressive strength has been reduced.
- The compressive strength of concrete is increased upto a maximum of 6.97%, 12.5% and 9.68% at 20% replacement fly ash, 10% replacement of GGBS and 2.5% of silica fume in cement content at 7 days, 14days and 28 days of curing respectively. By further addition of silica fume to the 20% fly ash and 10% GGBS replaced cement; the compressive strength has been reduced.
- The compressive strength of concrete is increased upto a maximum of 6.97%, 12.09% and 10.07% at 20% replacement fly ash, 10% replacement of GGBS, 2.5% of silica fume and 2.5% of metakaolin in cement content at 7 days, 14days and 28 days of curing respectively. By further addition of metakaolin to the 20% fly ash and 10% GGBS and 2.5% silica fume replaced cement, the compressive strength has been reduced.

8. REFERENCES

- [1] Dr. D. V. Prasada Rao, N.Lakshmi Narayana, 2017 “Properties of multi component composite cement concrete” IJERGS, Volume 5, Issue 1, January-February, 2017, ISS 2091-2730, pg no. 54-61
- [2] Balakrishna.Y, V.Lavanya, Naresh. A ,S.vijaya Bhaskar Reddy 2016 “Study the combined effect of Micro silica and GGBS on compressive, split tensile and flexural strength in concrete by partial replacement of cement” IRJET, Vol. 3.
- [3] S. Vijaya Bhaskar Reddy, Dr. P. Srinivasa Rao 2016, “Influence of micro silica and GGBS on compressive strength of blended with two supplementary cementing materials in concrete” IJERT, Vol. 5, Issue 03, March-2016
- [4] B. Raghunath Reddy, N.R.Gowthami, 2016 “Effect of Fly ash and nano GGBS on the properties high strength concrete”, IJETMR, december-2016, pg no.484-489.
- [5] Anusha Suvana, Prof .P.J. Salunke, Prof. N.G.Gore & Prof. T.N.Narkehde 2015, “Cement replaced pozzolanas in fibre reinforced concrete “ IJSTE, Vol. 2, Issue 4, October-2015.